



# AGS 3502

ART. NO: 3502 | GRAFFITI PROTECTION

A water-carried all-weather long-term protection, formulated for most types of surfaces. Provides extra strong protection against spray paint, marker/felt-tip pens and mechanical damage. Also provides protection against airborne pollution and moisture. Correctly applied, life expectancy against graffiti is approximately 7 years and can be increased up to 10 years. Permeable and allows the protected surface to breath. Prevents graffiti from penetrating into the surface. A so called sacrificial coating, which means that surface must be re protected, following graffiti removal. **AGS 3502** is readily biodegradable according to OECD test 302 B.

## INSTRUCTIONS FOR USE

### Preparation

Clean off both graffiti and other contamination, such as traffic dirt, wax, oil and paint residue etc. from the surface. Mask and protect windows in a suitable manner. Ideal temperature for external application should be between 10-35°C. Minimum temperature is +5°C. Relative humidity must not exceed 95%.

**NB!** Fresh concrete has to cure for at least 28 days before protection.

### Exterior protection

Shake or stir product well prior to use. **AGS 3502** can be applied with a low-pressure sprayer or airless spray gun. The protection is applied 2-3 times..

**NB!** Allow some drying between applications.

**AGS 3502** can be applied to a damp, not wet surface. Runs and/or excessive application can easily be washed off with water, following completion of work.

**NB!** Minimum 3 applications of **AGS 3502** when a 10 year protection is desired.

### Exterior Graffiti removal

#### Method 1 - Normal substrate

Remove graffiti with hot water and high-pressure (90°C & 90-150 bar / 1300-2175 PSI). In difficult cases, AGS graffiti removers are used in conventional manner. Re-protect cleaned area.

#### Method 2 - Sensitive substrate

Apply [AGS 3505](#) with a low-pressure sprayer. Allow a few minutes for the protection remover to act and then rinse off with hot water (60-90°C & 60-80 bar/870-1160 PSI). The method is most suitable when surface is brittle. Any graffiti left on the surface can be removed with [AGS 3505](#) on a cloth. The cleaned area should be wiped with a cloth and water. Re-protect cleaned area.

### Re-protection of cleaned surface

When removing graffiti, the protective coating is also normally removed. Re-protect 2-3 times with **AGS 3502**.

Modified: 2021-11-22

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and are responsible for the result.

#### **Dosage**

Use as concentrate.

#### **Consumption**

Varies depending upon type of surface material. It's porosity and capillary ability etc.

#### **Guidelines**

- Concrete, brick or similar surfaces, a total consumption for 3 layers will be 0,25-0,3 ltr/m<sup>2</sup>.
- Sandstone, plaster or other soft absorbent surfaces, a total consumption for 3-4 layers will be 0,3-0,4 ltr/m<sup>2</sup>.

#### **Drying-period**

The protected surface will be water- and graffiti-resistant after 2 hours and dry after 4 hours. Ultimate protective effect will be achieved after 72 hours.

#### **Appearance on surface**

Transparent, mostly invisible dependent on type of surface. UV- resistant. Weather-, water-, and graffiti - resistant.

**NB!** Some building materials can darken or become shiny.

#### **Storage**

Store frost-free in closed original container.

#### **Shelf life**

Approximately 12 months in unopened container.

#### **Precautions**

Use protective clothing and glasses.

#### **Technical data**

- White water-carried dispersion.
- Packaging: 5 or 25 litre plastic jerricans.
- Density: 1,00 kg/ltr.
- Odourless.
- pH-value approx. 8.0
- Contains: wax, alcohol ethoxylated.

#### **Marking**

Not classified.

Not classified as dangerous goods according to **ADR**.

For more information, see [MSDS](#).

**Modified: 2021-11-22**

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and are responsible for the result.